

HOT ROLLED AND COLD DRAWN ROUNDS

Size, Inches	Weight Per Foot, Pounds	Estimated Weight 20' Bar	Size, Inches	Weight Per Foot, Pounds	Estimated Weight 20' Bar	Size, Inches	Weight Per Foot, Pounds	Estimated Weight 20' Bar
1/8	.042	.84	2-1/8	12.06	241.2	4-1/4	48.23	964.6
3/16	.094	1.88	2-3/16	12.78	255.6	4-5/16	49.66	993.2
1/4	.167	3.34	2-1/4	13.52	270.4	4-3/8	51.11	1022.2
5/16	.261	5.22	2-5/16	14.28	285.6	4-7/16	52.58	1051.6
3/8	.376	7.52	2-3/8	15.06	301.2	4-1/2	54.08	1081.6
7/16	.511	10.22	2-7/16	15.87	317.4	4-9/16	55.59	1111.8
1/2	.668	13.36	2-1/2	16.69	333.8	4-5/8	57.12	1143.4
9/16	.845	16.90	2-9/16	17.53	350.6	4-11/16	58.68	1173.6
5/8	1.04	20.80	2-5/8	18.40	368.0	4-3/4	60.25	1205.0
11/16	1.26	25.20	2-11/16	19.29	385.8	4-7/8	63.46	1270.4
3/4	1.50	30.00	2-3/4	20.19	403.9	4-15/16	65.10	1302.0
13/16	1.76	35.20	2-13/16	21.12	422.4	5	66.76	1335.2
7/8	2.04	40.80	2-7/8	22.07	441.4	5-1/16	68.44	1368.8
15/16	2.35	47.00	2-15/16	23.04	460.8	5-1/8	70.14	1402.8
1	2.67	53.40	3	24.03	480.6	5-3/16	71.86	1437.2
1-1/16	3.01	60.20	3-1/16	25.05	501.0	5-1/4	73.60	1472.0
1-1/8	3.38	67.60	3-1/8	26.08	521.6	5-5/16	75.36	1507.2
1-3/16	3.77	75.40	3-3/16	27.13	542.6	5-3/8	77.15	1543.0
1-1/4	4.17	83.40	3-1/4	28.21	564.2	5-7/16	78.95	1579.0
1-5/16	4.60	92.00	3-5/16	29.30	586.0	5-1/2	80.78	1615.6
1-3/8	5.05	101.00	3-3/8	30.42	608.4	5-5/8	84.49	1689.8
1-7/16	5.52	110.40	3-7/16	31.55	631.0	5-3/4	88.29	1765.8
1-1/2	6.01	120.20	3-1/2	32.71	654.2	5-7/8	92.17	1843.4
1-9/16	6.52	130.40	3-9/16	33.89	677.8	5-15/16	94.14	1882.8
1-5/8	7.05	141.00	3-5/8	35.09	701.8	6	96.13	1922.6
1-11/16	7.60	152.00	3-11/16	36.31	726.2	6-1/4	104.31	2086.2
1-3/4	8.18	163.60	3-3/4	37.55	751.0	6-1/2	112.82	2256.4
1-13/16	8.77	175.40	3-13/16	38.81	776.2	6-3/4	121.67	2423.4
1-7/8	9.39	187.80	3-7/8	40.10	802.6	7	130.85	2617.0
1-15/16	10.02	200.40	3-15/16	41.40	828.0	7-1/2	150.21	3006.0
2	10.68	213.60	4	42.73	854.6	8	170.90	3418.0
2-1/16	11.36	227.20	4-1/8	45.44	908.8	9	216.30	4326.0
			4-3/16	46.73	930.6	10	267.00	5340.0